Buderus | Edelstahl

Buderus Corrosion-Resistant Plastic Mould Steel 2085 MOD

	C	Si	Mn	P	S	Cr	Ni	Mo	others
Typical analysis	0.28	0.30	0.95	0.030	0.050	14.2	~ 0.50	1.10	+
Chemical composition as per SEL	0.28–0.38	≤ 1.00	≤ 1.40	≤ 0.030	0.050–0.100	15.0–17.0	≤ 1.00	/	

Figures in % by mass

Register of European Steels (SEL)	X 33 CrS 16
DIN EN ISO 4957	~ Z 33 CS 16
AISI	~ 422 + S

Characteristics

Corrosion-resistant, sulphur-alloyed plastic mould steel with modified chemical composition and increased hardness in comparison to 1.2085 Standard.

Applications

Mould frames and mould fittings for corrosion-resistant injection-moulding dies.
Not suitable for contouring mould parts.

Note: Because of its controlled sulphur content (economic to machine) and the high hardness level, this material has low toughness properties.

Delivered condition

Quenched and tempered to 340–385 HB (≙ approx. 1150–1300 MPa)*

Physical properties (reference values)

Thermal expansion coefficient (10^{-6}/K)	20–100 °C 10.0	20–250 °C 12.0	20–500 °C 13.2
Thermal conductivity (W/mK)	20 °C 23.0	250 °C 24.0	500 °C 25.0
Young's modulus (GPa)	20 °C 215	250 °C 203	500 °C 180




* Surface hardness in Brinell, converted to DIN EN ISO 18265, Table A.1

Buderus Edelstahl GmbH | Steel Bar Sales | Buderusstraße 25 | D-35576 Wetzlar
Telephone +49 (0) 64 41-374 2468 | Fax +49 (0) 64 41-374 2784 | info@buderus-steel.com | www.buderus-steel.com


2085 MOD

Heat treatment		
Stress relieving	Temperature: Duration: Cooling:	Approx. 500 °C in the quenched and tempered state 1 hour per 50 mm wall thickness Furnace
Soft annealing	Temperature: Duration: Cooling:	820 °C 1 hour per 25 mm wall thickness Furnace
Hardening	Temperature: Duration:	1030 °C 1 minute per mm wall thickness
Quenching hardness	Max. 53 HRC	in oil or vacuum
Tempering	Temperature: Duration: Cooling:	See tempering curve 1 hour per 25 mm wall thickness Air
Working hardness	~ 340–385 HB	


Tempering curve



Effect of the tempering temperature on corrosion resistance



TTT curve (continuous)



Legal notice. Buderus Edelstahl GmbH has taken every possible care in compiling this information; the data is nevertheless subject to intervening changes. Buderus Edelstahl GmbH disclaims all liability and any warranty as regards the accuracy, currency, correctness and completeness of the information provided. The information provided is merely descriptive and indicative in nature, and binding only when expressly agreed as undertakings in a contract made with Buderus Edelstahl GmbH. Buderus Edelstahl GmbH moreover reserves the right to make changes at any time without prior notice. Buderus Edelstahl GmbH disclaims all liability for loss or damage of any kind, including consequential loss, arising in connection with use of the information provided. This publication supersedes all previous ones.
© Buderus Edelstahl GmbH, Wetzlar, 06/2012